



1100 - PRODUCT DATA SHEET

Nexalloy 1100 is 99% aluminum filler typically used on similar base metal such as 1060, 1070, 1080, 1100, 1350 and 3003

NEXAL WELDING PRODUCTS APPROVALS AND SPECIFICATIONS

AWS A5.10 classification ER1100, R1100

Chemical Composition (weight %)

Aluminum	99.0 Min
Manganese	0.50 Max
Iron + Silicon	0.95 Max
Copper	0.05-0.20
Beryllium	0.0001 Max

Elements 0.05 Max & Total 0.15 Max

Typical Properties

Melting Range	1090 – 1215 F	643 – 657 C
Density	.098 lbs\cu in. Other	
Post Anodize Color	White Gold	

Wire and Rod Diameters Available

0.030" 0.035" 3/64" 1/16" 3/32" 1/8" 5/32" 3/16" 1/4" 5/64"

Packaging Available

Plastic Spools – 1LB/0.4KG, 5LB/2.2KG, 10LB/4.5KG, 16LB/7.2KG, 20LB/9KG

Metal Spools – 10LB/4.5KG, 15LB /6.8KG **TIG Rods** – 5LB/2.2KG, 10LB/4.5KG, 50LB/22.6KG

Drums – 150LB/68KG, 300LB/136KG

MIG Welding Procedures: DCEP

Wire Diameter	WFS ipm	Amps	Volts	Consumption LB/100FT	Argon(cfh)
0.030"	480-625	60-175	15-24	0.65-1.25	25-30
0.035"	450-750	70-185	15-27	1.00-4.25	30-35
3/64"	330-500	125-260	20-29	1.00-4.25	35-45
1/16"	250-450	170-300	24-30	3.8-66	45-75
3/32"	160-200	275-400	26-31	35-66	60-85

TIG Welding Procedures: ACHF

Base Thickness	Filler Wire Size	Tungsten	Amps	Consumption LB/100FT	Gas Cup Size	Argon(cfh)
1/16"	1/16"	1/16"	60-80	0.75	3/8"	20
3/32"	3/32"	3/32"	85-120	1.00	3/8"	20
1/8"	3/32"	3/32"	125-160	1.50	3/8"	20
3/16"	1/8"	1/8"	190-220	4.5-6.0	7/16"	25
1/4"	5/32"	5/32"	200-300	8-10	1/2"	30
3/8"	3/16"	3/16"	330-380	15-20	5/8"	35
1/2"	1/4"	1/4"	400-500	25-40	5/8"	40

Nexal Aluminum Inc.
www.nexalloy.com

5938 Ambler Drive Mississauga, ON L4W 2N3
An ISO 9001:2008 Certified Company

Phone: 1-905-629-8282
Fax: 1-905-629-8532

The data and information contained or referenced is presented as typical results without guarantee or warranty and Nexal expressly disclaims liability incurred of any kind with reliance thereon

Aluminum Manufacturing since 1973